

Optimization of Process Parameters in Machining of Alloy Steel Using Nano Fluids

A.Venkata Vishnu¹, Jijo Sam², K Praveen kumar³, D Praveen⁴, B Vishnu⁵, G Aravind⁶

Asst.Professor¹, Asst.Professor², Asst.Professor³, Asst.Professor⁴, Asst.Professor⁵, Asst.Professor⁶

¹ Department of Mechanical Engineering, NNRG, Hyd, Telangana, India Student, Department of Mechanical Engineering, NNRG, Hyd, Telangana, India

Abstract

In machining process a lot of heat is developed due to the friction between tool and work piece, which will potentially damage the cutting tools as well as the work piece. To reduce the friction, heat transfer between tool and workpiece and to remove metal particles away from the cutting zone normally lubricants/cutting fluids are employed in metal cutting industries during machining operation. The objective of the present paper is to find out the set of optimal conditions for the selected process parameters, using a nano fluid. Taguchi method is used to determine the optimum cutting parameters viz. cutting speed, feed rate, depth of cut and type of tool at three different levels. The experiments are carried out using L₉ (3⁴) orthogonal array and the work piece selected is Alloy Steel. Nano fluids have novel properties that make them potentially useful in heat transfer medium at cutting zone.

Keyword: - Nano Fluid, Taguchi Method, Alloy steel, Turning cutting speed, feed rate, depth of cut and type of tool, etc.

1. INTRODUCTION:

Application of Nano fluid lubrication in cutting has proved to be feasible alternative to cutting fluids, if it can be applied properly. If the friction at the machining zone can be minimized by providing effective lubrication, the heat generated can be reduced to some extent. If a suitable lubricant can be successfully applied in the machining zone, it leads to process improvement. Several studies related to the lubrication properties of Nano fluids are carried out over the past several decades. The growing demand for higher productivity, product quality and overall economy in manufacturing by machining, insists high material removal rate and high stability and long life of the cutting tools. But machining with high cutting velocity, feed rate and depth of cut is inherently associated with generation of large amount of heat and high cutting temperature. Such high cutting temperature not only reduces dimensional accuracy and tool life but also impairs the surface integrity of the product by inducing tensile residual stresses, surface and subsurface micro-cracks in addition to rapid oxidation and corrosion.

2. EXPERIMENTAL SETUP:

The Literature survey helped in proper selection of the material and suitable method [1-8]. Taguchi Robust Design Methodology is used to determine the optimum conditions for the selected control parameters. Orthogonal Array and Signal to Noise

Ratio are employed to study the performance characteristics for the selected process parameters. The turning operations (facing) are carried out on CNC lathe at Balanagar, Hyderabad and the machine used is WASINO LJ-63m CNC Turning Machine shown in fig.no.1.

2.1. Selection of Work Material:-

The work piece material used is EN353 Alloy steel in the form of round bars of 32 mm diameter and length of 200 mm. Alloy steels are widely used as machining components in various industries. This material has significant application in automotive industry. Typical applications of this material are crown wheel, crown pinion, bevel pinion, bevel wheel, timing gears, king pin, pinion shaft, differential turning etc. The gears especially crown wheel and pinion are one of the most stress prone parts of a vehicle, which are made of Alloy steel.

2.2. Selection of Insert:

The cutting inserts used for machining are VNMG, TNMG and CNMG carbide tools of KORLEY Company, which are Gold coated, and uncoated Carbide tools.



Fig. No: 1 CNC Lathe



Fig. No. 2: EN353 Alloy Steel



Fig. No. 3 Rockwell hardness machine

2.3. Selection of Lubricant

Selection of cutting fluid is important in order to maintain better tool life, less cutting forces, lower power consumption, high machining accuracy and better surface integrity etc. Here Nano fluid, is used as cutting fluid under .

2.4. Preparation of Nano Fluids

In the present work Boric acid (H_3BO_3) Nano particles are mixed with water, as a base fluid used is water, to make H_3BO_3 Nanofluid. Five grams of H_3BO_3 , Nano particles and directly mix with 100 ml of water as a base fluid.

3. EXPERIMENTAL DESIGN

The four control factors Cutting Speed (A), Feed Rate (B) and Depth Of Cut(C) and type of tool(D) are selected with three levels and the corresponding orthogonal array L₉ (3⁴) is chosen and are tabulated in Table No.2. Alloy Steel bars

of 32mm diaX200mm length are prepared for conducting the experiment. Using different levels of the Process parameters as per the experimental design shown in table no.2, the specimens have been machined using conventional lathe accordingly; the Hardness of the material is measured precisely.

Table No. 1: Control Factors & Levels for Flooded

Factors /Levels	Speed (A) (rpm)	Feed (B) (mm/min)	Depth Of Cut (C) (mm)	Type of tools (D)
1	1000	0.1	0.1	T-I
2	1500	0.2	0.3	T-II
3	2000	0.3	0.5	T-III

Table No. 2. Experimental Design with corresponding results & S/N ratios

S.No	Cutting Speed (rpm)	Feed (mm/rev)	Depth of Cut (mm)	Type of Tool	RHN	S/N RATIO
	A	B	C	D		
1	1000	0.1	0.1	T-I	65	36.25
2	1000	0.2	0.3	T-II	56	34.96
3	1000	0.3	0.5	T-III	53	34.48
4	1500	0.1	0.3	T-III	79	37.94
5	1500	0.2	0.5	T-I	66	36.39
6	1500	0.3	0.1	T-II	68	36.65
7	2000	0.1	0.5	T-II	73	37.26
8	2000	0.2	0.1	T-III	70	36.90
9	2000	0.3	0.3	T-I	74	37.38

4.RESULTS & DISCUSSIONS:

Hardness is a characteristic of a material, not a fundamental physical property. It is defined as the

resistance to indentation, and it is determined by measuring the permanent depth of the indentation. More

simply put, when using a fixed force (load) and a given indenter, the smaller the indentation, the harder the material.

Hardness is measured precisely with the help of a Rockwell hardness tester equipment and the results are tabulated in table no 2. For each experiment the corresponding S/N values are also tabulated. Optimization of Hardness is carried out using Taguchi method. Confirmatory test have also been conducted to validate optimal results.

The best condition for cutting speed is level 3 (37.18), for feed is level 1 (37.15), for depth of cut is level 2 (36.76) and type of tool is level 1 (36.67). Thus, the optimum conditions chosen were: **A3-B1-C2-D1**. A confirmation test is performed with the obtained optimum cutting, the Hardness is measured and the S/N ratio is calculated for the flooded condition. The conformation test results are tabulated in the table no 5.

Table No 3: Summary of S/N Ratios for flooded

Factor	Level 1	Level 2	Level 3
Speed(A)	36.38	36.99	37.18
Feed(B)	37.15	36.08	36.17
Depth of Cut(C)	36.6	36.76	36.04
Type of tool(D)	36.67	36.29	36.49

Table No 4: Optimum Set of Control Factors for flooded condition

Factors /Levels	Speed (A) (rpm)	Feed (B) (mm/min)	Depth Of Cut(C) (mm)	Type of tool (D)
Optimum Value	2000	0.1	0.3	T-I

From table no. 4 the following calculations are done, for all the cases the predicted value is calculated in the same procedure.

$$\begin{aligned} \eta_{\text{predicted}} &= Y + (A3-Y) + (B1-Y) + (C2-Y) + (D1-Y) \\ &= A3+B1+C2+D1-3Y \\ &= [(37.18) + (37.15) + (36.76) + (36.67)] - [3X (36.46)] \\ \eta_{\text{predicted}} &= 38.38 \end{aligned}$$

Therefore, the predicted average for optimum condition of hardness is 38.38.

5. CONCLUSIONS:

A confirmation test is performed with the obtained optimum cutting parameters for cutting speed is level 3 (37.18), for feed is level 1 (37.15), for depth of cut is level 2 (36.76) and type of tool is level 1 (36.67). The

Hardness value is measured and the S/N ratio is calculated for this condition. The conformation test and the predicted values are tabulated in the table no 5 & 6.

Hardness Values	S/N RATIO
76	37.62

Table No 5: Conformation Test Results

η predicted	38.38
η conformation	37.62

Table No. 6: Comparison Of S/N Ratios

The objective of the present paper is to find out the set of optimum conditions in order to improve Hardness, using Taguchi methodology considering the turning parameters for the Alloy Steel material. Based on the results of the present experimentation the following conclusions are drawn:

- In the present experimentation the optimum speed under flooded conditions is obtained using Taguchi Robust Design Methodology is 2000 rpm. Similarly the results obtained for feed and depth of cut are 0.1mm/min and 0.3mm respectively. The corresponding Type of tool is T-I.
- The S/N ratio of predicted value and verification test values are valid when compared with the optimum values. It is found that S/N ratio value of verification test is within the limits of the predicted value and the objective of the work is full filled.

REFERENCES

- [1] Leskover, p; Grum, J. (1986). The metallurgical aspect of machining, Annals of CIRP 35/1, 537-550
- [2] A .Venkata Vishnu, K B G Tilak, Manik Reddy, "Optimization of Process Parameters for Surface Roughness in CNC Turning of EN-36 Material Using Taguchi Robust Design Methodology", International Journal of Core Engineering & Management (IJCEM), ICCEMT-2015, ISSN: 2348-9510, Special issue, December-2015. pp: 89-104
- [3] Nirav M. Kamdar, Prof. Vipul K. Patel, "Experimental Investigation of Machining Parameters of EN36 Steel", International Journal of Engineering Research and Applications (IJERA) ISSN: 2248-9622. Vol. 2, Issue 3, May-Jun 2012, pp.1833-1838.
- [4] Kaushal Pratap Singh and Girish Dutt Gautam: "Selection of Optimum Machining Parameters for EN36 Alloy Steel in CNC Turning Using Taguchi Method" International Journal of Scientific & Engineering Research, Volume 5, Issue 3, ISSN 2229-5518 – March 2004
- [5] Manan Kulshreshtha: "Analysis of the Effect of Machining Parameters on Surface Roughness of EN 36 Nickel Steel", International Journal of Advanced Information Science and Technology (IJAIST) ISSN: 2319:2682 Vol.16, No.16, August 2013.
- [6] A .Venkata Vishnu, G. Guruvaiah Naidu, K B G Tilak, J.Ramakrishna, "Application of Taguchi Method in the Optimization of Turning Parameters for Material Removal Rate of En-36 Material", International Journal of Advance Engineering and Research Development E-ISSN (O): 2348-4470 P-ISSN (P): 2348-6406, Volume 2, Issue 8, August-2015.
- [7] Ballal, Inamdar and Patil P.V. "Application Of Taguchi Method For Design Of Experiments In Turning Gray Cast Iron " International Journal of Engineering Research and Applications (IJERA) Vol. 2, Issue 3, May-Jun 2012, pp.1391-1397.
- [8] G. Guruvaiah Naidu, A.Venkata Vishnu, G.Janardhana Raju "Optimization of Process Parameters for Surface Roughness in Milling of EN-31 Steel Material Using Taguchi Robust Design Methodology", International Journal of Mechanical And Production Engineering ISSN: 2320-2092, Vol.2 Issue 9, September-2014.
- [9] A.Venkata Vishnu, K B G Tilak, G. Guruvaiah Naidu, Dr.G.Janardhana Raju "Optimization of Different Process Parameters of Aluminium Alloy 6351 in CNC Milling Using Taguchi Method", International Journal of Engineering Research and General Science, ISSN: 2091-2730,Nepal, Vol.3 Issue 2, March-April-2015.
- [10] Lathkar, G., S; Kharde, R. R; Basu, S. K. (2001). Some experiments in machining grease based solid lubricants, Journal of the Institution of Engineers, (India), vol. 82, 01-06
- [11] Edemir, A. (1991). Tribological properties of boric acid and boric acid forming surfaces, Part I. Crystal Chemistry and Mechanism of self lubrication of boric acid, Lubrication Engineering. Vol. 47, 168-178
- [12] HMT "Production Technology", Tata McGraw Hill, 2004.
- [13] Phillip j. Ross "Taguchi Techniques for Quality Engineering", Tata McGraw Hill, Second Edition, 2005.
- [14] A.Venkata Vishnu1 G.Guruvaiah Naidu S.Sai Reddy Y.Purna Chander Rao T.Kranthi Kiran

Experimental Investigation of Turning of Steel Alloy Under Sae40+Boric Acid (IJSRD/Conf/RTIME/2016/009).

- [15] A.Venkata Vishnu “An Investigation on Comparison of Vegetable Oil and Nano Fluids Coolants in Turning of En 19 Alloy Steel”, International Journal of Pure and Applied Research in Engineering and Technology IJPRET, 2017 (UGC Approved); Volume 6 (4): November 2017, pp: 1-15.
- [16] A.Venkata Vishnu, G.Kiran Kumar, “Analysis of surface roughness in turning using nano fluids: Prediction

model and cutting parameters optimization”, IJRASET (UGC Approved) Volume 5, Issue XII, December 2017,pp 340-347.

- [17] A.Venkata Vishnu, G.Guruvaiah.Naidu "Optimization of Process Parameters for Cutting Temperature In Milling Of En-19 Alloy Steel", International Journal Of Creative Research Thoughts (IJCRT) (UGC Approved), Issn: 2320-2882, Volume.6, Issue 1, Feb 2018, Page No.246-250.