International Journal of Research in Advent Technology, Vol.6, No.6, June 2018
E-ISSN: 2321-9637
Available online at www.ijrat.org

A Critical Review on Synthesis of Zinc Oxide (ZnO) Nanostructures by Hydrothermal method

Neel A. Patel[1]
Department of physics, Veer Narmad South Gujarat University, Surat, India[1],
Research Scholar [1]
Email: Neelpatel5533@yahoo.com [1]

Abstract- Nanostructured ZnO materials have received great interest from researcher due to their remarkable performance in electronics, optics and pharmaceutical industries. This paper presents studies of hydrothermal technique of preparation of nanostructured Zinc Oxide. In the next part of this review properties of synthesized Zinc Oxide are described.

Keywords - Zinc Oxide, Synthesis, Hydrothermal method.

1. INTRODUCTION:

Zinc Oxide is multifunctional material with its unique physical and chemical properties, such as high chemical stability, high electrochemical coupling coefficient, broad range of radiation absorption and high photostability [1] [2]. In materials science, Zinc Oxide is classified as a semiconductor in group II-VI, whose covalence is on the boundary between ionic and covalent semiconductors. A broad energy band (3.37eV), high bond energy (60 meV) and high thermal and mechanical stability at room temperature make it attractive for potential use in electronics, optoelectronics and laser technology [3][4]. ZnO particles can be synthesized through various methods by controlling the synthesis parameters. The properties can be tailored by shape and size, resulting in renewable applications relevant to their structural properties. Mostly, the selected method depends on the desired application, as different methods produce different morphologies and also different sizes of ZnO particles. Accordingly, the chemical and physical parameters such as the solvent type, precursors, pH, and the temperature were highly considered. An assortment of ZnO nanostructures with different growth morphologies such as nanorods, nanosphere, nanotubes, nanowires, nanoneedles and nanorings have been successfully synthesized. [5].

2. SYNTHESIS OF ZINC OXIDE BY HYDROTHERMAL METHOD:

The hydrothermal method does not require the use of organic solvents or additional processing of the product like grinding and calcination, which makes it a simple and environmentally friendly technique. The process takes place in an autoclave, in this synthesis mixture of substrates is heated gradually to a temperature of 100–300°C and left for several days. Crystal nuclei are formed and grow as a result of heating followed by cooling. This process has many advantages, including the possibility of carrying out the synthesis at low temperatures, the diverse shapes and dimensions of the resulting crystals depending on the composition of the starting mixture and the process temperature and pressure, the high degree of crystallinity of the product, and the high purity of the material obtained [12] [13].

In this review the hydrothermal methods of synthesis of zinc oxide will be discussed. With the hydrothermal method, synthesized ZnO has variety of structures and it offers a wide range of properties. These methods are described in detail in the following sections (Table 1).

Table 1. Summary of Hydrothermal method of obtaining Zinc Oxide.

Method	Precursors	Synthesis Conditions	Properties and Applications	References
Hydrothermal method	$ZnCl_2$, NaOH	Reaction: 5–10 h, 100–220 °C in Teflon-lined autoclave	Particles Morphology: bullet-like (100–200nm), rod-like (100–200 nm), sheet (50–200 nm), polyhedron (200–400nm), crushed stone-like (50–200 nm)	[6]

Hydrothermal Method	$Zn(CH_3COO)_2$, $Zn(NO_3)_2$, LiOH, KOH, NH4OH	Reaction time: 10–48h, 120–250 °C	hexagonal (wurtize) structure, Size of microcrystalline: 100 nm - 20 μm	[7]
Hydrothermal Method	$Zn(CH_3COO)_2$, NaOH, HMTA (hexamethylenetetra amine)	Reaction time:5–10 h, 100–200°C; HMTA concentration: 0–200 ppm	spherical shape; particles diameter: 55–110 nm	[11]

A hydrothermal process was used by Chen D. et al. [6] using $ZnCl_2$ and NaOH in a ratio of 1:2 to obtain ZnO particles with different morphology like bullet, road, sheet, polyhedron and crushed stone. This synthesis was done in teflone line autoclaves at temperature 100 °C to 220 °C with reaction time 5 to 10 hours. The process took place by way of reaction (1) and (2):

$$ZnCl_2 + 2NaOH \rightarrow Zn(OH)_2 + 2Na^+ + 2Cl^- \quad \ldots\ldots (1)$$

$$Zn(OH)_2 \rightarrow ZnO + H_2O \quad \ldots\ldots..(2)$$

Size and the morphology of the resulting ZnO particles were studied using an X-ray diffractometer (XRD) and transmission electron microscope (TEM). The temperature and time of reaction were shown to have a significant effect on the structure and size of the ZnO particles. It was also found that as the pH of the solution increases, there is an increase in the crystallinity and size of the particles, which reduces the efficiency of the process.

A hydrothermal process was also used by Dem Yamets et al. [7], synthesized nanocrystalline ZnO has different particle sizes (100 nm–20 μm) with hexagonal wurtize structure. The process was carried out in an autoclave, in isothermal conditions or at variable temperature (120–250 °C).Increasing the time of the hydrothermal process caused an increase in the diameter of the ZnO particles. It was observed that an increase in temperature by 50–70 °C enabled a fourfold reduction in the time of the experiment, which is a very favorable phenomenon.

Ismail A, et al. [11] used a hydrothermal method to synthesize nanocrystalline zinc oxide. This synthesis was done at temperature 100 °C to 200 °C with reaction time 5 to 10 hours Obtained zinc oxide by way of the following reactions (3) and (4):

$$Zn(CH_3COO)_2 + 2NaOH \rightarrow Zn(OH)_2 + 2CH_3COONa \quad \ldots\ldots(3)$$

$$Zn(OH)_2 \rightarrow ZnO + H_2O \quad \ldots\ldots..(4)$$

The shape of the ZnO particles is affected by the time and temperature of the process. With an increase in time, temperature and surfactant concentration, the size of the particles increases. Hydrothermal processing of the precursor, followed by drying, produced spherical particles of ZnO with sizes in the range 55–110 nm depending on the conditions of synthesis.

3. CONCLUSIONS:

This study shows that ZnO Structure with different grain size can be obtain by controlling the concentration of precursors, temperature and time of growth. Meanwhile with hydrothermal method we get nanostructured ZnO with different Surface Area and different morphologies, Surface Area and Morphology of ZnO plays a critical role in many application such as Photo-emitters, Transducers, Actuators, varistors, sensors, and catalysts by optimizing the dimension of ZnO Nanoparticle. Zinc Oxide is also very useful material because of its many interesting properties like, a wide range of UV absorption, high photostability, biocompatibility and biodegradability. ZnO can also be obtained with a variety of particle structures through hydrothermal method, which determine its applications in a wide range of fields of technology. Therefore a hydrothermal method of synthesizing crystalline Zinc Oxide which can be used on an industrial scale has become a subject of growing interest in science as well as industry.

4. FUTURE SCOPE OF WORK:

- Synthesis of ZnO nanoparticle under various condition and study their optical properties.
- Synthesis of ZnO thin film to study their property for solar cell and optoelectronic device.
- Rare earth (Ce, Dy and Er) doped ZnO nanoparticle find variety of applications in spintronics device.

5. ACKNOWLEDGMENTS:

The Author expresses his sincere gratitude towards Prof. Dr. I. B. Patel, Department of Physics, Veer Narmad South Gujarat University, for his valuable suggestions and thanks to Head of Department of physics, Veer Narmad South Gujarat University, Surat for gave us necessary facilities.

REFERENCES

[1] Segets, D.; Gradl, J.; Taylor, R.K.; Vassilev, V.; Peukert, W. Analysis of optical absorbance spectra for the determination of ZnO nanoparticle size distribution, solubility, and surface energy. ACS Nano 2009, 3, 1703–1710.

[2] Lou, X. Development of ZnO series ceramic semiconductor gas sensors. J. Sens. Trans. Technol. 1991, 3, 1–5.

[3] Bacaksiz, E.; Parlak, M.; Tomakin, M.; Özcelik, A.; Karakiz, M.; Altunbas, M. The effect of zinc nitrate, zinc acetate and zinc chloride precursors on investigation of structural and optical properties of ZnO thin films. J. Alloy. Compd. 2008, 466, 447–450.

[4] Wang, J.; Cao, J.; Fang, B.; Lu, P.; Deng, S.; Wang, H. Synthesis and characterization of multipod, flower-like, and shuttle-like ZnO frameworks in ionic liquids. Mater. Lett. 2005, 59, 1405–1408.

[5] AmnaSirelkhatim,Shahrom Mahmud. Review on Zinc Oxide Nanoparticles: Antibacterial Activity and Toxicity Mechanism. Nano-Micro Lett. (2015) 7(3):219–242.

[6] Chen, D.; Ciao, X.; Cheng, G. Hydrothermal synthesis of zinc oxide powders with different morphologies. Solid State Commun. 2000, 113, 363–366

[7] Dem'Yanets, L.N.; Li, L.E.; Uvarova, T.G. Zinc oxide: Hydrothermal growth of Nano- and bulk crystals and their luminescent properties. J. Mater. Sci. 2006, 41, 1439–1444.

[8] Music, S.; Ivanda, M. Precipitation of ZnO particles and their properties. Mater. Lett. 2005, 59, 2388–2393.

[9] Zhang, J.; Wang, J.; Zhou, S.; Duan, K.; Feng, B.; Weng, J.; Tang, H.; Wu, P. Ionic liquid controlled synthesis of ZnO microspheres. J. Mater. Chem. 2010, 20, 9798–9804.

[10] Hu, X.L.; Zhu, Y.J.; Wang, S.W. Sonochemical and microwave-assisted synthesis of linked single crystalline ZnO rods. Mater. Chem. Phys. 2004, 88, 421–426.

[11] Ismail, A.A.; El-Midany, A.; Abdel-Aal, E.A.; El-Shall, H. Application of statistical design to optimize the preparation of ZnO nanoparticles via hydrothermal technique. Mater. Lett. 2005, 59, 1924–1928.

[12] Djurišcić, A.B.; Chen, X.Y.; Lung, Y.H. Recent progress in hydrothermal synthesis of zinc oxide nanomaterials. Recent Pat. Nanotechnol. 2012, 6, 124–134

[13] Tsuzuki, T.; Dawkins, H.; Dunlop, J.; Trotter, G.; Nearn, M.; McCormick, P.G. Nanotechnology and cosmetic chemist. Cosmet. Aeorosol Toilet. Aust. 2002, 15, 10–24.

[14] N. A. Patel , I. B. Patel "Qualitative studies of ZnO nanoparticles grown by hydrothermal technique" IJRCS, vol 2 Jan 2018, 11-13 (Arrow)

[15] P. M. Aneesh, K. A.Vanaja, M. K. Jayaraj, Synthesis of ZnO nanoparticles by hydrothermal method Nanophotonic Materials IV, edited by Zeno Gaburro, Stefano Cabrini, Proc. of SPIE Vol. 6639, 66390J, (2007).

[16] A.Ramachandra Reddy, A. N. Mallika, K. Sowri Babu, and K. Venugopal Reddy (2015) "Hydrothermal Synthesis and Characterization of Zno Nano Crystals" , IJMMME, Volume 3, Issue2

[17] S.R.Brintha, M.Ajitha "Synthesis and characterization of ZnO nanoparticles via aqueous solution, sol-gel and hydrothermal methods" IOSR Journal of Applied Chemistry (IOSR-JAC) (Nov. 2015), PP 66-72

[18] G.C.Yi, C. Wang (2005) "ZnO nanorods: synthesis, characterization and applications" Semicond. Sci. Technol. 20, S22–S34